

COELAN^o-BOAT PRIMER

PRODUCT DESCRIPTION	
Features	One-component, glazing primer on the basis of polyurethane.
Colour	Yellowish (for teak and light wood) Reddish (for mahogany and reddish wood) Brownish (for oak wood and classic boats)
Packing units	250-ml-tins 1-litre-cans 5-litre-cans
Characteristics	Fast-curing. Subsequent coating works can take place already after approx. 2 – 3 hours.
Field of application	Primer for hardwood and soft wood.
Storage	Min. 12 months in closed original-containers stored in a dry place at temperatures between + 5 ° C and + 25 ° C. Direct sunlight is to be avoided. 24 hours before application, the material should be acclimated at temperatures between + 18 ° C and + 20 ° C. Opened containers have to be sealed off air tightly and firmly and should be used up as soon as possible.
PRODUCT DATA	
Density	Approx. 0,92 g/cm ³ ± 0,02 g/cm ³
Viscosity (+ 20 ° C)	Approx. 80 mPas
Consumption	Approx. 200 ml/m ² (depending on the absorbency of the substrate)
Flash point	23 ° C
Water vapour diffusion resistance figure	μ = 5.820

APPLICATION INSTRUCTIONS	
Suitable substrates	New wooden substrates. Different pigmentations are possible. Please also refer to our GUIDE TO BOAT COATING.
Surface preparation	The substrate subject to coating needs to be even, dry, clean, bearable, pore free, firm and free of loose particles, dust, oil, grease, rubber, silicone or any other loose or separating substances. In order to increase the absorbency of the substrate, it is recommended to sand new wood with emery paper of grain 80. Remove the sanding dust by means of a vacuum cleaner or a dry and clean cloth. Please do not use any solvents! Crosscut wood has to be pre-treated with an epoxy primer. Lips are to be rounded off in a radius of 2 mm.
Application	In order to ensure a proper deep priming and pore filling of the substrate, please apply the primer evenly in two coats by means of a foam roller or a brush. If very absorbent substrates are given, a higher amount of coats may become necessary. The colour intensity can be influenced by repeated paintings.
Working temperature	Temperature of material, air and substrate must be min. + 8 ° C and max. + 30 ° C. Relative air-humidity < 85 %. The temperature of the substrate should be at least 3 ° C above dew point.
Cleaning of tools	With COELAN®-THINNER FOR BOAT COATINGS.
IMPORTANT INFORMATION	
Danger information, danger classes, measures of precaution and information for disposal as per Safety Data Sheet.	

COELAN®-BOAT PRIMER

ISSUE: 12/01

To the best of our knowledge, the technical information contained on this product information is reliable. As the product may be used in conditions which we cannot foresee, this advice is not legally binding. Furthermore, we reserve the right to make technical changes in line with progress. On publication of revised special instructions for use, any existing technical information shall be invalid. For any queries, you may contact our special technical advice service. Agreements and warranties must in principle be in writing. Verbal agreements should therefore be confirmed in writing. In addition, our terms of delivery and payment apply.