

# COELAN<sup>®</sup> - FLEXO-PRIMER FOR BOAT COATINGS

<b>PRODUCT DESCRIPTION</b>	
<b>Features</b>	One-component primer on the basis of polyurethane.
<b>Colour</b>	Brownish-transparent.
<b>Packing units</b>	250-ml-bottles
<b>Characteristics</b>	Liquid primer. Not light stable. Only suitable where a coloured coating follows.
<b>Field of application</b>	Ready-to-use primer for plastic substrates, such as inflatable dinghies, fenders, tarpaulins, etc.
<b>Storage</b>	Min. 12 months in closed original-containers stored in a dry place at temperatures between + 5 ° C and + 25 ° C. Direct sunlight is to be avoided. 24 hours before application, the material should be acclimated at temperatures between + 18 ° C and + 20 ° C. Opened containers have to be sealed off air tightly and firmly and should be used up as soon as possible.
<b>PRODUCT DATA</b>	
<b>Density</b>	Approx. 0,94 g/cm <sup>3</sup>
<b>Consumption</b>	Approx. 50 - 70 ml/m <sup>2</sup>
<b>Drying time (+ 20 ° C)</b>	Min. 30 minutes, max. 6 hours!
<b>APPLICATION INSTRUCTIONS</b>	
<b>Suitable substrates</b>	Elastic substrates in the boat sector. Due to the high amount of different plastic surfaces, compatibility and adhesion tests are required prior the application!
<b>Surface preparation</b>	The substrate subject to coating needs to be even, dry, clean, bearable, pore free, firm and free of loose particles, dust, oil, grease, rubber, silicone or any other loose or separating substances. It is recommended to sand the surface slightly with emery paper of grain 80.

<b>APPLICATION INSTRUCTIONS</b>	
<b>Application</b>	To be rubbed-on thinly and evenly by means of a dry and clean cloth. Please wear solvent-resistant gloves during the application!
<b>Working temperature</b>	Temperature of material, air and substrate must be min. + 8 ° C and max. + 30 ° C. Relative air-humidity < 85 %. The temperature of the substrate should be at least 3 ° C above dew point.
<b>Cleaning of tools</b>	With COELAN®-UNIVERSAL CLEANER.
<b>IMPORTANT INFORMATION</b>	
Danger information, danger classes, measures of precaution and information for disposal as per Safety Data Sheet.	

COELAN®-FLEXO-PRIMER FOR BOAT COATINGS

ISSUE: 08/02

To the best of our knowledge, the technical information contained on this product information is reliable. As the product may be used in conditions which we cannot foresee, this advice is not legally binding. Furthermore, we reserve the right to make technical changes in line with progress. On publication of revised special instructions for use, any existing technical information shall be invalid. For any queries, you may contact our special technical advice service. Agreements and warranties must in principle be in writing. Verbal agreements should therefore be confirmed in writing. In addition, our terms of delivery and payment apply.